



DOWEX UPCORE Mono A-500

A Uniform Particle Size, Strong Base Anion Exchange Resin Specifically Designed for the UPCORE System

Product	Type	Matrix	Functional group
DOWEX* UPCORE* Mono A-500	Type 1 strong base	Styrene-DVB, gel	Quaternary amine

Guaranteed Sales Specifications		Cl ⁻ form
Total exchange capacity, min.	eq/l	1.3
	kg/ft ³ as CaCO ₃	28.4
Water content	%	50 - 58
Bead size distribution [†]		
Mean particle size	µm	575 ± 50
Uniformity coefficient, max.		1.1
>850µ, max.	%	5
<300µ, max.	%	0.5
Whole uncracked beads, min.	%	95

Typical Physical and Chemical Properties		Cl ⁻ form
Total swelling (Cl ⁻ -OH ⁻)	%	20
Particle density	g/ml	1.08
Shipping weight	g/l	670
	lbs/ft ³	42

Recommended Operating Conditions	
Maximum operating temperature:	
OH ⁻ form	60°C (140°F)
Cl ⁻ form	100°C (212°F)
pH range	0-14
Bed depth, min.	1200 mm (4 ft)
Pressure drop, design max.	1.5 bar (22 psi)
Pressure drop, max.	2.5 bar (37 psi)
Flow rates:	
Service/fast rinse	5-60 m/h (2-24 gpm/ft ²)
Regeneration/displacement rinse	4-10 m/h (1.6-4 gpm/ft ²)
Total rinse requirement	2-4 Bed volumes
Regenerant	2-5% NaOH

[†]For additional particle size information, please refer to the Particle Size Distribution Cross Reference Chart (Form No 177-01775/CH 171-476-E).

*Trademark of The Dow Chemical Company

Typical properties and applications:

DOWEX* UPCORE* Mono A-500 strong base anion resin is a uniform particle size, gellular, type 1 anion resin designed for use in the UPCORE packed bed counter-current regeneration system.

The absence of large beads in DOWEX UPCORE Mono A-500 resin

results in high operating capacity and good resistance to silica fouling.


DOWEX UPCORE Mono A-500 resin has an excellent resistance to mechanical and osmotic stress which helps minimize resin attrition.

Packaging

25 liter bags or 5 cubic feet fiber drums.

Figure 1. Pressure Drop Data

Temperature = 20° C (68° F)



For other temperatures use:

$$P_T = P_{20^\circ\text{C}} / (0.026 T_{^\circ\text{C}} + 0.48), \text{ where } P \equiv \text{bar/m}$$

$$P_T = P_{68^\circ\text{F}} / (0.014 T_{^\circ\text{F}} + 0.05), \text{ where } P \equiv \text{psi/ft}$$

Warning: Oxidizing agents such as nitric acid attack organic ion exchange resins under certain conditions. This could lead to anything from slight resin degradation to a violent exothermic reaction (explosion). Before using strong oxidizing agents, consult sources knowledgeable in handling such materials.

Notice: No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

Published April 2002.

