

AmberLyst™ 125 Polymeric Catalyst

Industrial-grade, Strongly Acidic Catalyst

Description

AmberLyst™ 125 Polymeric Catalyst is a clean, gel, sulfonic acid polymeric catalyst with a uniform particle size and a low crosslinked structure. It is highly active for condensation reactions such as the condensation of phenol with acetone to produce Bisphenol-A [U.S. Patent 5,233,096 (1993)].

AmberLyst™ 125 is designed to produce high-quality BPA. Its particle size and pore structure allow for reduced pressure drop and notably longer lifetime than conventional catalysts.

Applications

- Condensation (Bisphenol-A)

Typical Properties

Physical Properties	
Copolymer	Styrene-divinylbenzene
Matrix	Gel
Type	Strong acid cation
Functional Group	Sulfonic acid
Physical Form	Light brown, translucent, spherical beads
Chemical Properties	
Ionic Form as Shipped	H ⁺
Concentration of Acid Sites ‡	≥ 4.80 eq/kg ≥ 0.70 eq/L
Water Retention Capacity	77 – 83%
Particle Size §	
Particle Diameter	1050 ± 50 µm
Uniformity Coefficient	≤ 1.10
< 900 µm	≤ 1%
Shrinkage (in solvent)	
Phenol	68%
Density	
Shipping Weight	730 g/L

‡ Dry Weight Capacity ≥ 4.80 eq/kg; Total Exchange Capacity (on a water-wet basis) ≥ 0.70 eq/L

§ For additional particle size information, please refer to the [Particle Size Distribution Cross Reference Chart \(Form No. 45-D00954-en\)](#).

Suggested Operating Conditions

Maximum Operating Temperature	130°C (265°F)
Bed Depth, min.	600 mm (2.0 ft)
Pressure Drop, max.	1 bar (15 psig) across the bed
Flowrates	
Linear Hourly Space Velocity (LHSV)	0.5 – 5 h ⁻¹
Backwash	See Figure 1

Hydraulic Characteristics

Estimated bed expansion of AmberLyst™ 125 Polymeric Catalyst as a function of backwash flowrate at a water temperature of 25°C (77°F) is shown in Figure 1.

Estimated pressure drop for AmberLyst™ 125 as a function of service flowrate at a water temperature of 25°C (77°F) is shown in Figure 2. These pressure drop expectations are valid at the start of the service run with clean water.

Figure 1: Backwash Expansion

Temperature = 25°C (77°F)





Figure 2: Pressure Drop

Temperature = 25°C (77°F)



Product Stewardship

DuPont has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with DuPont products—from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

DuPont strongly encourages its customers to review both their manufacturing processes and their applications of DuPont products from the standpoint of human health and environmental quality to ensure that DuPont products are not used in ways for which they are not intended or tested. DuPont personnel are available to answer your questions and to provide reasonable technical support. DuPont product literature, including safety data sheets, should be consulted prior to use of DuPont products. Current safety data sheets are available from DuPont.

Please be aware of the following:

- **WARNING:** Oxidizing agents such as nitric acid attack organic ion exchange resins under certain conditions. This could lead to anything from slight resin degradation to a violent exothermic reaction (explosion). Before using strong oxidizing agents, consult sources knowledgeable in handling such materials.



info@lenntech.com Tel. +31-152-610-900
www.lenntech.com Fax. +31-152-616-289

All information set forth herein is for informational purposes only. This information is general information and may differ from that based on actual conditions. Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where DuPont is represented. The claims made may not have been approved for use in all countries. Please note that physical properties may vary depending on certain conditions and while operating conditions stated in this document are intended to lengthen product lifespan and/or improve product performance, it will ultimately depend on actual circumstances and is in no event a guarantee of achieving any specific results. DuPont assumes no obligation or liability for the information in this document. References to "DuPont" or the "Company" mean the DuPont legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. No freedom from infringement of any patent or trademark owned by DuPont or others is to be inferred.

© 2022 DuPont. DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours Inc., unless otherwise noted.

