


DuPont™ AmberTec™ UP9600 Ion Exchange Resin

Semiconductor Grade Weak Base Anion Exchange Resin

Description

DuPont™ AmberTec™ UP9600 Ion Exchange Resin is a macroporous, weak base anion exchange resin developed specifically for use in producing ultrapure water for the semiconductor industry. It is intended for use in packed bed and floating bed demineralization systems prior to reverse osmosis.



AmberTec™ UP9600 receives extra cleaning steps during the manufacturing process in order to reduce the quantity of trace leachable organic materials that are present in the standard industrial version. Therefore, it can immediately produce high-quality water in the first operation cycle.

The chemical properties and particle size of AmberTec™ UP9600 have been optimized to help yield excellent operating capacity and rinse characteristics, while reducing chemical regenerant and water usage. The very stable structure and limited reversible swelling of the resin make it very resistant to osmotic shock. The high degree of porosity of this resin provides efficient adsorption of large organic molecules, as well as their desorption during regeneration, thus allowing excellent protection against organic fouling of the strong base anion exchange resin.

Applications

- Demineralization in Ultra Pure Water, ideally when treating water with:
 - High organic fouling potential
 - High percentage of mineral acidity (FMA)
- Partial demineralization when weak acid removal is not required

System Designs

Compatible with the following system technologies and bed configurations:

- Co-current
- Counter-current / Hold-down
- Layered beds

Typical Properties

Physical Properties

Copolymer	Styrene-divinylbenzene
Matrix	Macroporous
Type	Weak base anion
Functional Group	Tertiary amine
Physical Form	Off-white, opaque, spherical beads

Chemical Properties

Ionic Form as Shipped	Free base (FB)
Total Exchange Capacity	≥ 1.25 eq/L
Water Retention Capacity	59.0 – 65.0%

Particle Size ^s

Particle Diameter	440-590 μm
Uniformity Coefficient	≤ 1.6
< 300 μm	$\leq 1.0\%$
> 710 μm	$\leq 5.0\%$

Stability

Swelling	FB $\rightarrow$ HCl $\leq 15\%$
----------	----------------------------------

Density

Shipping Weight	670 g/L
-----------------	---------

For additional particle size information, please refer to the [Particle Size Distribution Cross Reference Chart](#) (Form No. 45-D00954-en).

Suggested Operating Conditions

Temperature Range (FB form)	5 – 60°C (41 – 140°F)
pH Range	
Service Cycle	0 – 6
Stable	0 – 14

For additional information regarding recommended minimum bed depth, operating conditions, and regeneration conditions for [separate beds](#) (Form No. 45-D01131-en) in water treatment, please refer to our Tech Fact.

Hydraulic Characteristics

Estimated bed expansion of DuPont™ AmberTec™ UP9600 Ion Exchange Resin as a function of backwash flowrate and temperature is shown in Figure 1.

Estimated pressure drop for AmberTec™ UP9600 as a function of service flowrate and temperature is shown in Figure 2. These pressure drop expectations are valid at the start of the service run with clean water and a well-classified bed.

Figure 1: Backwash Expansion

Temperature = 10 – 60°C (50 – 140°F)





Figure 2: Pressure Drop

Temperature = 10 – 60°C (50 – 140°F)



Product Stewardship

DuPont has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with DuPont products—from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

DuPont strongly encourages its customers to review both their manufacturing processes and their applications of DuPont products from the standpoint of human health and environmental quality to ensure that DuPont products are not used in ways for which they are not intended or tested. DuPont personnel are available to answer your questions and to provide reasonable technical support. DuPont product literature, including safety data sheets, should be consulted prior to use of DuPont products. Current safety data sheets are available from DuPont.

Please be aware of the following:

- **WARNING:** Oxidizing agents such as nitric acid attack organic ion exchange resins under certain conditions. This could lead to anything from slight resin degradation to a violent exothermic reaction (explosion). Before using strong oxidizing agents, consult sources knowledgeable in handling such materials.



info@lennotech.com Tel. +31-152-610-900
www.lennotech.com Fax. +31-152-616-289

All information set forth herein is for informational purposes only. This information is general information and may differ from that based on actual conditions. Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where DuPont is represented. The claims made may not have been approved for use in all countries. Please note that physical properties may vary depending on certain conditions and while operating conditions stated in this document are intended to lengthen product lifespan and/or improve product performance, it will ultimately depend on actual circumstances and is in no event a guarantee of achieving any specific results. DuPont assumes no obligation or liability for the information in this document. References to "DuPont" or the "Company" mean the DuPont legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. No freedom from infringement of any patent or trademark owned by DuPont or others is to be inferred.

© 2023 DuPont. DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours Inc., unless otherwise noted.

