

Lewatit® C 267 is a premium grade, standard cross-linked, gel, strong acid cation exchange resin based on a styrene/DVB polymer. **Lewatit® C 267** is specially suited for industrial water treatment applications including demineralization. **Lewatit® C 267** can be used in both single bed and mixed bed applications. **Lewatit® C 267** features a high ion exchange capacity combined with excellent mechanical and osmotic stabilities. **Lewatit® C 267** is supplied in the form of spherical beads (protonated and fully swollen) with a heterodisperse particle size distribution. **Lewatit® C 267** has a minimum content of fines (up to 50 mesh particles) resulting in low pressure drops during operation.

Lewatit® C 267 is supplied in the protonated form. It is also available in its sodium form which is called **Lewatit® C 249** then.

Lewatit® C 267 complies with 21 CFR 173.25 of the FDA regulations covering the application of ion exchange resins as secondary direct food additives. Details regarding the correct use of **Lewatit® C 267** in food application (21 CFB 173.25) can be obtained from Lanxess, Business Unit Ion Exchange Resins.

The special properties of this product can only be fully utilized if the technology and process used correspond to the current state-of-the-art. Further advice in this matter can be obtained from Lanxess, Business Unit Ion Exchange Resins.

General Description

Ionic form as shipped	H ⁺
Functional group	Sulfonic acid
Matrix	DVB / Styrene
Structure	Gel
Appearance	Brown/black, translucent

Physical and Chemical Properties

		metric units	
Total capacity*	H-Form	min. eq/l	1.9
Uniformity Coefficient*		max.	1.6
Bead size*	> 90 %	mm	0.3 - 1.25
Effective size		mm	0.52 (+/- 0.06)
Bulk density	(+/- 5 %)	g/l	800
Density		approx. g/ml	1.25
Water retention*		wt. %	49 - 54
Volume change	H ⁺ --> Na ⁺	max. vol. %	- 7
Stability	at pH-range		0 - 14
Stability	temperature range	°C	1 - 140
Storability	of the product	max. years	2
Storability	temperature range	°C	-20 - +40

* Specification values subjected to continuous monitoring.

Trace Elements Analysis

Recommended Operating Conditions*

		metric units	
Operating temperature		max. °C	140
Operating pH-range			0 - 14
Bed depth		min. mm	800
Pressure drop		max. kPa	
Linear velocity	exhaustion	max. m/h	5 - 50
Bed expansion	backwash (20 °C)	approx. % per m/h	4
Freeboard	backwash (extern / intern)	vol. %	65 - 75
Volumetric flow rate	exhaustion	BV/h	8 - 48
Regenerant	type		HCl / H ₂ SO ₄
Regenerant	level	approx. g/l	48 - 320
Regenerant	concentration	approx. wt. %	0.5 - 6
Linear velocity	regeneration	m/h	1 - 10
Linear velocity	rinse, slow / fast	m/h	1 - 10 / 5 - 50
Volumetric flow rate	regeneration	BV/h	4 - 12
Volumetric flow rate	rinse, slow / fast	approx. BV/h	2.5 - 8 / 8 - 48
Rinse water requirement	slow / fast	approx. BV	1 - 2 / 2 - 5

* The recommended operating conditions refer to the use of the product under normal operating conditions. It is based on tests in pilot plants and data obtained from industrial applications. However, additional data are needed to calculate the resin volumes required for ion exchange units. These data are to be found in our Technical Information Sheets.

** Regeneration progressive

** After regeneration the listed TOC and resistivity figures might not be achieved again.

*** 100m/h for polishing

Additional Information & Regulations

Safety precautions

Strong oxidants, e.g. nitric acid, can cause violent reactions if they come into contact with ion exchange resins.

Toxicity

The safety data sheet must be observed. It contains additional data on product description, transport, storage, handling, safety and ecology.

Disposal

In the European Community ion exchange resins have to be disposed, according to the European waste nomenclature which can be accessed on the internet-site of the European Union.

Storage

It is recommended to store ion exchange resins at temperatures above the freezing point of water under roof in dry conditions without exposure to direct sunlight. If resin should become frozen, it should not be mechanically handled and left to thaw out gradually at ambient temperature. It must be completely thawed before handling or use. No attempt should be made to accelerate the thawing process.

This information and our technical advice – whether verbal, in writing or by way of trials – are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.



WATER TREATMENT SOLUTIONS

info@lennotech.com Tel. +31-152-610-900

www.lennotech.com Fax. +31-152-616-289

For more information or a quote, please use the

Contact Form