

TRISEP® X-20™


LENNTECH
 WATER TREATMENT SOLUTIONS


Low Fouling RO Membrane

TRISEP® X-20™ flat sheet is a fouling-resistant membrane with a unique, proprietary formulation that results in low fouling characteristics. The unique barrier layer chemistry does not degrade over time like some competitive “fouling resistant” membranes that are simply “modified” or “coated” standard membranes. Excellent for wastewater and other high fouling applications, X-20 membrane offers consistent high salt rejection while lowering cleaning frequency and extending membrane life. X-20 membrane sheet is available in both dry and wet flat sheet rolls.

MEMBRANE CHARACTERISTICS

Membrane Chemistry	Backing Material	Stabilized Salt Rejection (%)	Minimum Salt Rejection (%)
Thin-Film Polyamide	Non-Woven Polyester	99.5	99.0

Flux Range LMH (GFD) ^a	Thickness (µm)	pH Range	Chlorine Tolerance ^b
47.6 – 71.4 (28.0 – 42.0)	130 – 170	1.0 – 12.0	< 0.1 ppm

a Test conditions: 2,000 ppm NaCl, 15.5 bar (225 psi), 25°C (77°F), 15% recovery, pH 8.0, 30 minutes operation. Membrane specifications may change without notice as design revisions occur.

b Oxidizing agents, such as free chlorine, in contact with polyamide membranes may result in shortened operating life or membrane failure.

IMPORTANT INFORMATION

Standard Sizes: TRISEP flat sheet membrane is available in a sample size of 305 mm x 1,016 mm (12 in x 40 in) and in a nominal roll size of 305 m x 1,016 mm (1,000 ft x 40 in). Custom lengths may be available on request.

Initial Flush: MICRODYN-NADIR recommends flushing membrane for 30 minutes and discarding permeate during the flush prior to operation.

Storage: Membrane is shipped dry unless wet membrane is specifically requested. Membrane shipped dry should be stored in a cool, dry place. If shipped wet, TRISEP membrane must remain sealed and refrigerated prior to use. Please see Membrane Storage Guide – Flat Sheet Membrane (TSG-O-011).

Contact


LENNTECH
 WATER TREATMENT SOLUTIONS

info@lenntech.com Tel. +31-152-610-900

www.lenntech.com Fax. +31-152-616-289