

Product Description

Membrane material	Polysulfone
Membrane type	RM33PS with proteins molecular weight cut-off (MWCO) of over 20,000 Daltons
Design	Spiral wound
Features	Shrink film-wrapped (-F)

Specification


*

Test conditions: 0,1% solution of myoglobin (17 kDa) in 0,9% solution of NaCl, P=0,1 MPa, T=25 °C. Recovery -15%
Membrane's specific flow by demineralized water (SDI<1) is min. 150 l/(hr*m2*0,1 MPa)

Model	Rejection by protein*, %	Area		Spacer	
		m2	ft2	mm	mil
8040-F20-1	97*	39	420	0,71	28
8040-F20-2	97*	37	400	0,79	31
8040-F20-3	97*	35	375	0,86	34

Operating conditions

Recommended operation pressure, MPa	0,2-1,5
Maximum operation pressure, MPa	2,1
Maximum pressure drop, MPa	0,1
Operation temperature, °C ¹⁾	4-50
pH at operation ¹⁾	1-12
CIP pH (short time operation)	1-13
Acceptable free Chlorine concentration during disinfection (not longer than 30 min), mg/l	200
Maximum feed flow, m3/hr	18
Concentrate/permeate ratio on each element, min	5:1
Turbidity, NTU max	1



Model	A mm	B mm	B' (ATD) mm	C mm	Weight kg
8040-F20-1/2/3	1016	203	200	28,6	14

LENNTECH

info@lennotech.com Tel. +31-152-610-900
www.lennotech.com Fax. +31-152-616-289