

Product Data Sheet

DIAION™ SA10DL

DIAION™ SA10DL is a gel type strongly basic anion exchange resin. It has a higher cross-linkages and excellent properties. A wide range of applications, especially in a field of manufacturing and processing pure water, is recommended.

Product

Grade Name	DIAION™ SA10DL
Type	Strong Base Anion
Matrix	Styrene-DVB, Gel
Functional Group	Type I (trimethyl ammonium groups)
Ionic Form	Cl ⁻

Specification

Whole Bead Count	-	90 min.
Salt Splitting Capacity	meq/mL	1.3 min.
Water Content	%	38 - 43
Particle Size Distribution on 1180 μm	%	5 max.
Particle Size Distribution thr. 500 μm	%	5 max.
Effective Size	mm	0.50 min.
Uniformity Coefficient	-	1.6 max.

Typical Properties

Shipping Density	g/L	690
Mean Particle Size	μm	660
Particle Density	g/mL	1.08
Total Swelling (Cl ⁻ to OH ⁻)	%	22

Recommended Operating Conditions

Maximum Operating Temperature	°C	80 (Cl ⁻) 60 (OH ⁻)
Operating pH Range		0 - 14
Minimum Bed Depth	mm	800
Service Flow Rate	m/h	10 - 60
Regenerant		NaOH
Regenerant Concentration	%	NaOH 2 - 8
Regenerant Level	g/L	50 - 200
Regenerant Flow Rate	m/h	2 - 8
Total Rinse Requirement	BV	2 - 10



Hydraulic Characteristics

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of DIAION™ SA10DL resin in normal down flow operation is shown in the graphs below.




Fig. 1 Pressure Drop of SA10DL




Fig. 2 Bed Expansion of SA10DL

Notice

This information are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. The application, use and processing of our products are beyond our control and therefore your own responsibility.