

Product Data Sheet

DIAION™ UBK08

DIAION™ UBK08 is a cation exchange resin with a uniform particle size. It has standard cross-linkages and excellent properties. A wide range of applications, especially in a field of manufacturing and processing pure water, is recommended.

Product

Grade Name	DIAION™ UBK08
Type	Strong Acid Cation
Matrix	Styrene-DVB, Gel
Functional Group	Sulfonic acid
Ionic Form	Na ⁺

Specification

Whole Bead Count	-	90 min.
Salt Splitting Capacity	meq/mL	2.0 min.
Water Content	%	43 - 49
Average Diameter	μm	600 ± 50
Uniformity Coefficient	-	1.10 max.

Typical Properties

Shipping Density	g/L	840
Particle Density	g/mL	1.28
Total Swelling (Na ⁺ to H ⁺)	%	9

Recommended Operating Conditions

Maximum Operating Temperature	°C	120
Operating pH Range		0 - 14
Minimum Bed Depth	mm	800
Service Flow Rate	m/h	10 - 40
Regenerant		HCl H ₂ SO ₄
Regenerant Concentration	%	HCl 4 - 10 H ₂ SO ₄ 1 - 4
Regenerant Level	g/L	30 - 150
Regenerant Flow Rate	m/h	2 - 10
Total Rinse Requirement	BV	2 - 10



DIAION™ UBK08

Hydraulic Characteristics

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of DIAION™ UBK08 resin in normal down flow operation is shown in the graphs below.




Fig. 1 Pressure Drop of UBK08




Fig. 2 Bed Expansion of UBK08

Operational Capacity Data




Fig. 3 Operational Capacity Data of UBK08
Regenerant : 4 % HCl

Notice

This information are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. The application, use and processing of our products are beyond our control and therefore your own responsibility.