

Macroporous Type I Strong Base Anion Exchange Resin

Basic Features:

Application	Demineralization - Mixed Bed - Indicator
Polymer Structure	Macroporous polystyrene crosslinked with divinylbenzene
Appearance	Spherical beads
Functional Group	Type 1 Quaternary Ammonium
Ionic form as shipped	OH ⁻

Typical Physical and Chemical Characteristics:

Total Capacity (min.)	Cl ⁻	1.15 eq/l
Total Capacity (min.)	Cl ⁻	25.11 kGr/ft ³
Moisture Retention	Cl ⁻	53-58 %
Mean Size Typical		0.65-0.90 mm
Uniformity Coefficient (max.)		1.70
Reversible Swelling (max.)	Cl ⁻ → OH ⁻	15 %
Specific Gravity		1.07 g/ml
Shipping Weight (approx.)		675-705 g/l
Temp Limit	OH ⁻	65 °C
Temp Limit	OH ⁻	150 °F
Temp Limit	Cl ⁻	100 °C
Temp Limit	Cl ⁻	212 °F
pH Limits		0-14 (Stability)
pH Limits	H ⁺	0-11 (Operating)

LENNTECH

info@lennotech.com

www.lennotech.com

Tel. +31-15-261.09.00

Fax. +31-15-261.62.89