

Mixed Bed Exchange Resin - Light Cation

Basic Features:

Application	EDM Applications - High Capacity
Polymer Structure	Gel polystyrene crosslinked with divinylbenzene
Appearance	Spherical beads
Functional Group	Sulphonic Acid and Type 1 Quaternary Ammonium
Ionic form as shipped	H ⁺ / OH ⁻

Typical Physical and Chemical Characteristics:

Cation Component	Gel Strong Acid Cation	
Anion Component	Gel Strong Base Anion	
Cation / Anion Ratio	50 / 50 %	
Total Capacity (min.)	Na ⁺	2.00 eq/l
Total Capacity (min.)	Na ⁺	43.70 kGr/ft ³
Total Capacity (min.)	Cl ⁻	1.30 eq/l
Total Capacity (min.)	Cl ⁻	28.40 kGr/ft ³
Moisture Content	62 %	
Mean Size Typical	0.60-0.85 mm	
Uniformity Coefficient (max.)	1.70	
Shipping Weight (approx.)	720-750 g/l	
Shipping Weight (approx.)	45-46.9 lbs/ft ³	
Temp Limit	Non-Regenerable Bed	100 °C
Temp Limit	Non-Regenerable Bed	212 °F
Temp Limit	Regenerable Bed	60 °C
Temp Limit	Regenerable Bed	140 °F
pH Limits	0-14	



info@lennotech.com

www.lennotech.com

Tel. +31-15-261.09.00

Fax. +31-15-261.62.89