

## PRODUCT DATA SHEET

# Purolite® MB500VC

Polystyrenic Gel, Macroporous,  
Mixed Bed Resin, Hydrogen form,  
Hydroxide form, With Indicator

## PRINCIPAL APPLICATIONS

- Demineralization - Mixed Bed

## ADVANTAGES

- Dyed Cation to indicate exhaustion



## SYSTEMS

- Coflow regenerated systems
- Counterflow regenerated systems
- Mixed Bed

## TYPICAL PACKAGING

- 1 ft³ Sack
- 25 L Sack
- 5 ft³ Drum (Fiber)

## TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

|                                        |                                                 |                                                         |
|----------------------------------------|-------------------------------------------------|---------------------------------------------------------|
| Appearance                             | Spherical Beads                                 |                                                         |
| Moisture Content (max.)                | 62 %                                            |                                                         |
| Particle Size Range                    | 300 - 1200 µm                                   |                                                         |
| < 300 µm (max.)                        | 1 %                                             |                                                         |
| Uniformity Coefficient (max.)          | 1.7                                             |                                                         |
| Shipping Weight (approx.)              | 700 - 735 g/L (43.8 - 45.9 lb/ft³)              |                                                         |
| Temperature Limit, Non-Regenerable Bed | 100 °C (212.0 °F)                               |                                                         |
| Temperature Limit, Regenerable Bed     | 60 °C (140.0 °F)                                |                                                         |
| Component Name                         | Gel Strong Acid Cation                          | Macroporous Type I Strong Base Anion                    |
| Polymer Structure                      | Gel polystyrene crosslinked with divinylbenzene | Macroporous polystyrene crosslinked with divinylbenzene |
| Functional Group                       | Sulfonic Acid                                   | Type I Quaternary Ammonium                              |
| Ionic Form                             | H <sup>+</sup> form                             | OH <sup>-</sup> form                                    |
| Cation / Anion Volumetric Ratio        | 40 %                                            | 60 %                                                    |



**LENNTECH**

info@lennotech.com Tel. +31-152-610-900  
www.lennotech.com Fax. +31-152-616-289