

Macroporous Strong Acid Cation Exchange Resin

Basic Features:

Application	Demineralization - Counter Flow / Polishing - Uniformly Sized
Polymer Structure	Macroporous polystyrene crosslinked with divinylbenzene
Appearance	Spherical beads
Functional Group	Sulphonic acid
Ionic form as shipped	H ⁺

Typical Physical and Chemical Characteristics:

Total Capacity (min.)	Na ⁺	1.80 eq/l
Total Capacity (min.)	Na ⁺	39.30 kGr/ft ³
Moisture Retention	H ⁺	54-59 %
Mean Size Typical		0.52-0.62 mm
Uniformity Coefficient (max.)		1.20
Reversible Swelling (max.)	Na ⁺ → H ⁺	4 %
Specific Gravity		1.18 g/ml
Shipping Weight (approx.)		725-765 g/l
Shipping Weight (approx.)		45.3-47.8 lbs/ft ³
Temp Limit	H ⁺	120 °C
Temp Limit	H ⁺	250 °F
Temp Limit	Na ⁺	140 °C
Temp Limit	Na ⁺	285 °F
pH Limits		0-14



info@lennotech.com

www.lennotech.com

Tel. +31-15-261.09.00

Fax. +31-15-261.62.89