

TRILITE® SM300

Ready to use mixed bed resin

Rev.3 Jan 2023

TRILITE® SM300 is a ready-to-use and highly regenerated mixed bed resin for high purity water application through the continuous ion exchange of cation and anion exchange resins.

TRILITE® SM300 is mixed bed resins of each component of strong acid cation exchange resin and strong base anion exchange resin in equivalent of cation and anion exchange capacity.

Physical and Chemical Properties

	SAC	SBA
Matrix	Styrene-DVB, Gel	
Functional group	Sulfonic acid	Type 1(Trimethylammonium)
Ionic form	H ⁺	OH ⁻
Particle Size(μm)	300~1,200	
Uniformity coefficient	1.6 ↓	
Ionic Conversion(%)	H ⁺	99.0 Min
	OH ⁻	95.0 Min
	Cl ⁻	1.0 Max
Mixed Ratio	1:1 (by equivalents) Cation : Anion	
Inlet condition	RO Outlet, Conductivity 10μs/cm, SV36	
Outlet condition	Guaranteed 17.0 MΩ·cm ↑ (in 10min.) Actual 18.0 MΩ·cm ↑ (in 10min.)	

Recommended Operating Conditions

Operating Temp(°C)	60	pH Range	0~14
Bed Depth(mm)	600	Service Flow Rate(m/h)	5~60

Applications

TRILITE® SM300 is widely used to get high purity water such applications R/O polisher, humidifier, and other applications requiring demineralized water.

All information contained in brochure is not absolute rather than relative one, created under the controlled environment by Samyang Corporation. Therefore, Samyang Corporation has no legal responsibility with respect to any and all information provided in brochure.



info@lennotech.com Tel. +31-152-610-900
 www.lennotech.com Fax. +31-152-616-289