

SEPLITE® Monojet™ SC3200 H+

Uniform particle size, Gel Strong acid cation resin for Industrial demineralization and condensate polishing applications

·Descriptions

SEPLITE® Monojet™ SC3200 H+ Ion Exchange Resin is a high cross-linkage product with excellent ion removal capability. Thanks to the uniform particle size and excellent chemical and physical properties, the resin have a long lifetime and offers a cost-effective simple operation. It is able to yield high operating capacity and help users to save the chemical regenerant and rinsing water.

SEPLITE® Monojet™ SC3200 H+ is compatible with co-current or counter-current systems as well as mixed bed or single bed. The resin could be available in Na+ form also.

·Physical and Chemical Characteristics

Matrix Structure	Gel, Styrene-divinylbenzene		
Functional group	Sulfonic acid		
Shipping form	H ⁺ (Na ⁺ is also available)		
Physical Appearance	Dark brown translucent spherical beads		
Particle size (mm)	0.65±0.05mm		
	<0.3mm	≤0.1%	
	≥0.85mm	≤3.0%	
Moisture content (%)	45-52 (H ⁺ Form)		
Total Capacity(eq/L)	≥2.0		
Bulk Density (g/l)	740-840		
Density (g/l)	1220-1250		
Whole beads count (%)	≥95		
Uniformity coefficient	≤1.1		
Volume change (Na ⁺ to H ⁺) Max. vol.%	7%		

·Applications

- Mixed bed polishing
- Industrial Demineralization
- Condensate polishing

PRODUCT INFORMATION

SEPLITE® Monojet™ SC3200 H+

Uniform particle size, Gel Strong acid cation resin for Industrial demineralization and condensate polishing applications



Recommended Operating Conditions

Operating Temperature	Max.	130°C	
PH Range		0-14	
Min. Bed depth	mm	800	
Operation linear velocity	max. m/h	5-60	
Backwash linear velocity	Approx. m/h	10-25 (at 20° C)	
Bed expansion	Approx. vol. %	4-5 (at 20° C, per m/h)	
Backwash Freeboard	vol. %	60-100	
Regenerant		HCl	H2SO4
Counter current regeneration level	Approx. g/l	50	80
Counter current regeneration concentration	Approx. wt. %	4-6	1-3
Regeneration linear velocity	Approx. m/h	5	5
Rinse linear velocity	Approx. m/h	5	5
Rinse water requirement(slow/fast)	BV	2-5	2-5
Co current regeneration level	Approx. g/l	100	150
Co current regeneration concentration	Approx. wt. %	6-10	1-3
Regeneration linear velocity	Approx. m/h	5	5
Rinse linear velocity	Approx. m/h	5	5
Rinse water requirement(slow/fast)	BV	4-8	4-8

PRODUCT INFORMATION

SEPLITE® Monojet™ SC3200 H+

Uniform particle size, Gel Strong acid cation resin for Industrial demineralization and condensate polishing applications



Hydraulic Characteristics

Typical values of pressure drop across a bed of SEPLITE® Monojet™ SC3200 are given for a range of operating flow rate in Fig. 1.

Fig. 2 shows the Bed expansion which is a function of flow rate and temperature. Be cautious to avoid loss by accidental over-expansion of the bed.

Fig. 1 Pressure Drop





Fig. 2 Backwash Expansion



Precautions

Resins should be stored in sealed containers or bags where temperature was above 0°C in dry conditions without exposure to direct sunlight.

Do not mix ion exchange resin with strong oxidizing agents; otherwise it will cause violent reactions.

In case of eyes contact with resins, rinse eyes immediately with plenty of water, and consult a specialist.

Material and samples must be disposed according to local regulations.

Dry polymers will expand when become wetted and may cause an exothermic reaction.

Spilled materials may be slippery.

SEPLITE® and Monojet™ are registered trademarks of Sunresin New Materials Co. Ltd., Xi'an

This information is general information and may differ from that based on actual conditions. For more information about SEPLITE® resins, please contact SUNRESIN® directly.

All information set forth herein is for informational purposes only. This information is general descriptive(introductory) information of SUNRESIN and its related products, technologies and services. Neither shall constitute the guarantee of SUNRESIN and its affiliates to products, technologies and services in specific fields and specific application conditions results, unless otherwise expressly noted. SUNRESIN and its affiliates assumes no obligation or liability for the information in this document. Customer is responsible for judging whether the information is appropriate for Customer's concrete demand and are obliged to understand whether the use of these products, technologies and services is permitted by the laws and regulations of their countries and relevant regions. Unless expressly stated, no freedom from infringement of use any patent or trademark or intellectual property rights owned by SUNRESIN or its affiliated companies under this document is to be inferred.